


WOVEN-SEAL

WOVEN CRAWL SPACE VAPOR BARRIER

Physical Properties and Typical Values

Property	Test Method	U.S. Value
Weight	ASTM D5261	6.4 oz/yd ² , 218 gsm
Breaking Strength warp	ASTM D5035	170 lb/in
Breaking Strength fill	ASTM D5035	135 lb/in
Grab Strength warp	ASTM D5034	230 lbf
Grab Strength fill	ASTM D5034	200 lbf
Trapezoidal warp	ASTM D4533	75 lbf
Trapezoidal fill	ASTM D4533	60 lbf
Tongue Tear warp	ASTM D2261	70 lbf
Tongue Tear fill	ASTM D2261	70 lbf
Mullen Burst	ASTM D3786	350 psi
Water Vapor Permeance	ASTM E96 Proc.	0.0172 perms
Antimicrobial Additive	--	Yes



*Woven 14 mil
Construction*

Woven-Seal is a 100% reinforced 14 mil vapor barrier is constructed using only premium, 100% virgin polyethylene. The high density woven reinforcement provides the maximum level of protection against punctures and tears. The woven polyethylene is then coated on both sides to provide not only a bright white top finish, but also give ideal protection against moisture and soil gas permeability.

Item #	Description
WS10008	8' x 100' Roll, 14 mil
WS10012	12' x 100' Roll, 14 mil